SECTION 02690 – PCC AGGREGATES

(Follow all instructions and make all edits with "Track Changes" turned on. If there are no instructions [orange text] above a subsection, paragraph, sentence, or bullet, then include it in the Project. Delete all orange text before preparing the final document. All other modifications to this Section will require ODOT Technical Resource and State Specifications Engineer approval.)

Comply with Section 02690 of the Standard Specifications modified as follows:

> ***(Use the following lead-in paragraph and subsection .40 when lightweight coarse aggregate is specified. Contact ODOT Structure Services prior to selecting internal curing.)***

Add the following subsection:

02690.40 Lightweight Coarse Aggregate - Provide lightweight coarse aggregate from the QPL.

> ***(Use the following lead-in paragraph and subsection .50 when lightweight fine aggregate is specified. Contact ODOT Structure Services prior to selecting internal curing.)***

Add the following subsection:

02690.50 Lightweight Fine Aggregate - Provide lightweight fine aggregate (LWFA) from the QPL. Maintain LWFA at or above saturated surface dry (SSD) condition by uniformly saturating and allowing drain down prior to batching and verify moisture condition by sampling and testing according to ODOT TM 249. Maintain the SSD condition during all batching operations.