



Sample No.	Width	Cu %	Sample No.	Width	Cu %
50-1	5.0'	.55	75-14	3.0'	.18
50-4	5.0'	.08	75-15	5.0'	.28
50-6	5.0'	.03	75-16	3.0'	<.05
50-7	5.0'	.01	75-17	4.0'	<.05
50-8	5.0'	.08	75-18	5.0'	<.05
66-20	17.5'	.13	75-19	9.0'	.63
66-21	16.0'	.14	75-20	5.0'	.12
66-22	17.5'	.01	75-21	10.0'	1.34
66-23	19.5'	.03	75-22	6.5'	1.31
66-24	7.8'	.03	75-23	6.5'	2.23
66-25	6.8'	.002	75-24	7.0'	.64
74-20	6.5'	.02	75-25	6.0'	.50
74-21	3.5'	.01	76-2	19.0'	.04
74-22	7.4'	.02	76-3	8.3'	.02
74-23	8.6'	.01	76-4	5.5'	.19
74-24	1.6'	.01	76-5	16.8'	.02
74-25	8.3'	.02	76-6	5.1'	.28
75-3	1.5'	<.03	76-7	9.6'	.02
75-4	6.5'	<.03	76-8	8.0'	.17
75-5	4.0'	<.03	76-9	5.5'	.03
75-6	2.5'	<.03	76-10	3.5'	.50
75-7	2.0'	<.03	76-11	5.0'	1.17
75-8	3.0'	<.03	76-12	4.0'	.19
75-9	2.0'	<.03	76-13	13.0'	.02
75-10	2.5'	<.03	76-14	5.0'	.66
75-11	14.0'	2.51	76-15	5.0'	.38
75-12	6.5'	2.71	76-16	10.0'	.54
75-13	2.5'	.68	76-17	2.0'	<.05

Sample No.	Width	Cu %
76-18	2.4'	<.05
76-19	16.0'	4.05
76-20	17.0'	4.05
76-21	5.3'	4.05
76-22	5.5'	.22
76-23	11.0'	4.05
76-24	6.0'	<.05
76-25	7.5'	.16

Figure 3.—Geologic and assay plan of Queen of Bronze mine, Takilma-Waldo district, Josephine County, Oregon.

P-150

Nov, 1951