

Location: Sec. 9, T. 7 S., R. 38 E.

Analysis:

West lens - 50' chip sample (P-7007)

Silica ( $\text{SiO}_2$ ) . . . . .	3.58%
Iron and alumina ( $\text{R}_2\text{O}_3$ ). . . . .	0.76%
Calcium carbonate ( $\text{CaCO}_3$ ). . . . .	94.38%
Magnesia ( $\text{MgO}$ ) . . . . .	0.22%
Phosphorus (P) . . . . .	0.018%

East Lens - 30' chip sample (P-7008)

Silica ( $\text{SiO}_2$ ) . . . . .	0.84%
Iron and alumina ( $\text{R}_2\text{O}_3$ ). . . . .	0.54%
Calcium carbonate ( $\text{CaCO}_3$ ). . . . .	96.80%
Magnesia ( $\text{MgO}$ ) . . . . .	0.47%
Phosphorus . . . . .	0.014%