sored Hill

Assayer

Golden Gate Mine Sec. 20, T. 37 S., R. 3 W.

per oz.

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

Grants Pass, Oregon *Bakerx Oregon* Sample submitted by A. O. S Sample description White of		PT on a Confidence (Security Confidence) on the space of the Space (Security Confidence) of the Confidence (Security Confidence) on the Confidence (Security Confidenc			Office Number AG-1414 November 8, 193 40 Grants Pass, Oregon greenstone. 2½ lbs. 2 inches.				
The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof. NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.									
	GOLD		SILVER					the the substantions must be a	
Sample Number	Ounces per ton	Value	Ounces per ton	Value	Percent	Value	Percent	Value	Total Value
	0.46	16.10	Trace						\$16.10
Market Quotations: Gold \$35.00per oz. Silver \$ per oz. \$ per oz.									