

Golden Sardine
 Jackson Co., Gold Hill District
 NE $\frac{1}{4}$ sec. 24, T. 35 S., R. 4 W.

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number BC-75 & 76

Grants Pass, Oregon

~~Baker, Oregon~~

February 7, 1937 41

Sample submitted by James W. Breeding Rogue River, Oregon

Sample description No. 1--Gray siliceous material and white quartz. 3 lbs.

$\frac{1}{2}$ inches and smaller. No. 2--Gray siliceous material. $\frac{1}{2}$ lbs. $\frac{1}{2}$ inches and smaller.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Percent	Value	Percent	Value	Total Value
	Ounces per ton	Value	Ounces per ton	Value					
1	0.18	6.30	Trace						\$6.30
2	0.03	1.05	Trace						\$1.05
					Nothing else of value.				

Market Quotations:

Gold $\$35.00$ per oz.
 Silver $\$$ per oz.
 $\$$ per oz.
 $\$$ per oz.

STATE ASSAY LABORATORY

 Assayer