Silver Tip

Gold Hill T. 36S., R. 4W., Sec. 19, 1/4 Sec. S. E.

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

Counts D.	0	ASSAY REPORT				Office Number BG-238			
Grants Pas Baker, Ora		+				March 28, 194/41			
Sample submitted by Mr.			Albert L. Miller						
Sample description Glassey white quartz and schistose, greenstone containing									
a large amount of iron oxide and a small amount of manganese oxide.									
The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof. NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.									
	GOLD		SILVER						
Sample Number	Ounces per ton	Value	Ounces per ton		Percent	Value	Percent	Value	Total Value
	0.03	\$1.05	0.04	\$.028					\$1.078
		· · · · · · · · · · · · · · · · · · ·							
	tations: \$ 35						STATE	ASSAY LA	BORATORY