

(20) A. G. 1471

GOLD HILL AREA

Assay reports by A. A. Lewis -- Manganese 11.7
Insoluble 63.6

Owner: A. Bailey

Location: Sec. 1, T. 37 S., R. 3 W.

Data: Sample submitted Nov. 30, 1940. Consisted mostly of iron oxide
and siliceous material with a small amount of manganese oxide.