

Golden Glow Mine
T. 33 S., R. 5 W., Secs. 15 & 21

Drumback

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number AG-1343
AG-1344

Grants Pass, Oregon

~~Baker, Oregon~~

October 18, 1940

Sample submitted by W. J. Barber Wolf Creek, Oregon

Sample description No. 16--Rusty quartz and altered felsite. 1 1/2 lbs. 1/2 inch.

No. 17--Altered rock, some rusty quartz. 1 lb. 3/4 inch.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Percent	Value	Percent	Value	Total Value
	Ounces per ton	Value	Ounces per ton	Value					
16	0.01	0.35	Trace						\$0.35
17	0.04	1.40	Trace						\$1.40

Market Quotations:

Gold \$ 35.00 per oz.
Silver \$ per oz.
\$ per oz.
\$ per oz.

STATE ASSAY LABORATORY

Assayer