

X
 Agness No. 1,2,3,4,5,6
 NW $\frac{1}{4}$ sec. 16, T. 37 S.,
 R. 9 W.
 Josephine Co., Illinois
 River

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number BC-147 & 148

Grants Pass, Oregon

~~Baker, Oregon~~

February 28, 1934

Sample submitted by Sigmund Dilsheimer, 2058 N.W. Flanders St., Portland, Oregon

Sample description No. 1--Chromite with a small amount of serpentine. 4 lbs. 3 inches and smaller. No. 2--Four pieces of nearly pure chromite.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Cr ₂ O ₃		Fe		Total Value
	Ounces per ton	Value	Ounces per ton	Value	Percent	Value	Percent	Value	
1					44.6		13.0		
2					40.0		11.4		

Market Quotations:

Gold	\$\$\$	per oz.
Silver	\$\$\$	per oz.
	\$\$\$	per oz.
	\$\$\$	per oz.

STATE ASSAY LABORATORY

Assayer

Agnes No. 1
Sec. 21, T. 37 S., R. 9 W.

Ill River

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number AG-1453
AG-1454

Grants Pass, Oregon
~~Beckers Oregon~~

December 2, 1940

Sample submitted by James H. McClung, Route 2, Box 792, Grants Pass, Oregon

Sample description Two pieces of chromite, one in each sample.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Chromic Oxide				Total Value
	Ounces per ton	Value	Ounces per ton	Value	Percent	Value	Percent	Value	
1					48.7				
2					46.1				

Market Quotations:

Gold \$ per oz.
Silver \$ per oz.
 \$ per oz.
 \$ per oz.

STATE ASSAY LABORATORY

Assayer

Happy Jack
T. 37S, R. 9W, Sec. 30
Illinois River

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

BG-306

ASSAY REPORT

Grants Pass, Oregon
Baker, Oregon

May 2 1941

Sample submitted by Chet M. Zachary, Selma, Oregon

Sample description: Four pieces of chromite with a considerable amount
of serpentine.

The assay results recorded below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results recorded below are from a sample furnished by the above named person. This Department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Chromic Oxide		Iron		Total Value
	Ounces per ton	Value	Ounces per ton	Value	Percent	Value	Percent	Value	
					31.2		10.1		

Market Quotations:

Gold \$ per oz.
Silver \$ per oz.
 \$ per lb.
 \$ per lb.

STATE ASSAY LABORATORY

Assayer

Red Hill Claim
T. 37S, R. 9W, Sec 28
Illinois River

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

BG-305

ASSAY REPORT

Grants Pass, Oregon
~~Grants Pass, Oregon~~

May 2 1941

Sample submitted by Low Hammer, Selma, Oregon

Sample description: Chromite with a small amount of serpentine.

6 lbs. 4 inches and smaller.

The assay results recorded below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results recorded below are from a sample furnished by the above named person. This Department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Chromic Oxide		Iron		Total Value
	Ounces per ton	Value	Ounces per ton	Value	Percent	Value	Percent	Value	
					52.4		11.8		

Market Quotations:

Gold \$ per oz.
Silver \$ per oz.
 \$ per lb.
 \$ per lb.

STATE ASSAY LABORATORY

Assayer

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number AG-1368

Grants Pass, Oregon

~~Baker, Oregon~~

November 6, 19~~3~~40

Sample submitted by Elwood Bullock, Route 1, Box 41, Cave Junction, Oregon

Sample description Rusty quartz containing a noticeable amount of pyrite and a small amount of molybdenite. 2½ lbs. 2 inches.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Qual. Nickel		Percent	Value	Total Value
	Ounces per ton	Value	Ounces per ton	Value	Percent	Value			
	Blank		Blank		Blank				

Market Quotations:

Gold \$ per oz.
 Silver \$ per oz.
 \$ per oz.
 \$ per oz.

STATE ASSAY LABORATORY

 Assayer

Josephine Mine
Sec. 36, T. 38 S., R. 9 W.

J. L. Rice

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number AG-1378
AG-1379

Grants Pass, Oregon

~~Baker, Oregon~~

November 8, 1940

Sample submitted by Robert Hanford, Redwoods Hotel, Grants Pass, Oregon

Sample description Two samples of black sand containing a large amount of magnetite.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Platinum		Percent	Value	Total Value
	Ounces per ton	Value	Ounces per ton	Value	Oz. per ton	Value			
1	1.30	45.50	0.8	0.56	0.22	8.80			\$54.86
2	0.10	3.50	Trace		Trace				\$ 3.50

Market Quotations:

Gold \$35.00 per oz.
Silver \$ 0.70 per oz.
Platinum \$40.00 per oz.
\$ per oz.

STATE ASSAY LABORATORY

Assayer

Gov't land
 Josephine Co., Ill. R. Dist.
 Sec. 2, T. 39 S., R. 9 W.

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number 1140

Grants Pass, Oregon

~~Baker Oregon~~

September 30 1939

Sample submitted by J. E. Morrison

Grants Pass, Oregon

Sample description Black sand concentrate.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER						Total Value
	Ounces per ton	Value	Ounces per ton	Value	Percent	Value	Percent	Value	
	0.51	17.85	Trace						\$17.85

Market Quotations:

Gold \$35.00 per oz.
 Silver \$ per oz.
 \$ per oz.
 \$ per oz.

STATE ASSAY LABORATORY

Assayer

Note: The above sample contained a small amount of platinum.

Smith Property
 Josephine Co., Ill. R. Dist.
 Sec. 14, T. 39 S., R. 8 W.

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number 368

Grants Pass, Oregon
 Baker, Oregon

April 25 1939

Sample submitted by J. S. Morrison, Mining Geologist Grants Pass, Oregon

Sample description Sample of limestone from property of Mr. Smith; known as the Holton Creek Limestone.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Insoluble		Percent	Value	Total Value
	Ounces per ton	Value	Ounces per ton	Value	Percent	Value			
					0.96				

Market Quotations:

Gold \$ per oz.
 Silver \$ per oz.
 \$ per oz.
 \$ per oz.

STATE ASSAY LABORATORY

 Assayer

Summit Group
 Josephine Co., Illinois River Dist.
 NW $\frac{1}{4}$ sec. 29, T. 38 S., R. 4 W.

July 8, 1938

ASSAY REPORT

Mr. J. E. Morrison, Mining Geologist
 State Assay Laboratory
 Grants Pass, Oregon

The following are the results of assays made on the samples taken from the McCaleb property.

<u>Office number</u>	<u>Sample number</u>	<u>Gold</u>		<u>Silver</u>		<u>Total Value</u>
		<u>Oz./ton</u>	<u>\$/ton</u>	<u>Oz./ton</u>	<u>\$/ton</u>	
719	Test Assay	Trace		Blank		
720	1 50w.	Trace		Blank		
721	2 50-100	0.01	0.35	Trace		0.35
722	3 100-150	Trace		Blank		
723	4 150-200	Trace		Blank		
724	5 200-250	Trace		Blank		
725	6 250-300	Trace		Blank		
726	7 300-350	0.01		Trace		0.35
727	8 350-400	Trace		Blank		

Gold @ \$35.00 / oz.

SIGNED

Casy Group
 Josephine Co., Ill. R. Dist.
 Sec. 7, T. 38 S., R. 9 W.

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number -114 & -115

Grants Pass, Oregon
~~Baker, Oregon~~

September 26, 1938

Sample submitted by J. E. Morrison, Mining Geologist -- Grants Pass, Oregon

Sample description Two samples from the property of R. E. McCalob.

No. 1; Tailing. No. 2; Concentrate.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Percent	Value	Percent	Value	Total Value
	Ounces per ton	Value	Ounces per ton	Value					
1	0.48	16.80	Trace						\$16.80
2	2.54	88.90	0.3	0.19					89.09

Market Quotations:

Gold \$ 35.00 per oz.
 Silver \$ 0.64 per oz.
 \$ per lb.
 \$ per lb.

State Assay Laboratory

Assayer

Agness No. 1
 Josephine Co., Illinois R
 Sec. 16 & 21, T. 37 S.,
 R. 9 W.

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY REPORT

Office Number BG-150

Grants Pass, Oregon

~~Baker Oregon~~

February 28, 1934

Sample submitted by Max E. Krueger, 4642 N.E. Halsey, Portland, Oregon

Sample description Two pieces of chromite.

The assay results given below are made without charge as provided by Chapter 176, Section 10, Oregon Laws 1937, the sender having complied with the provisions thereof.

NOTICE: The assay results given below are from a sample furnished by the above named person. This department had no part in the taking of the sample and assumes no responsibility, other than the accuracy of the assay of the material as furnished it by the sender.

Sample Number	GOLD		SILVER		Cr ₂ O ₃		Fe		Total Value
	Ounces per ton	Value	Ounces per ton	Value	Percent	Value	Percent	Value	
					45.3		13.0		

Market Quotations:

Gold \$ per oz.
 Silver \$ per oz.
 \$ per oz.
 \$ per oz.

STATE ASSAY LABORATORY

 Assayer