

WHITE PROSPECT

MARION

STATE DEPARTMENT OF GEOLOGY AND MINERAL INDUSTRIES

ASSAY LABORATORIES

Baker

SAMPLE INFORMATION REQUESTED

Grants Pass

The law passed by the Legislature, governing the free assaying and analyzing of samples sent to the State Assay Laboratories, provides that certain information be furnished the Laboratory regarding samples sent for assay, etc. A copy of this law will be found on the back of this blank. Please read the law carefully. Will you please fill in the information called for on the following blank, as far as possible and return the same to the nearest State Assay Laboratory along with your sample? If you have made out a blank, this copy is for your future use. Keep a copy of the information on each sample for your own reference.

Your name in full Ken White

Postoffice address Box 269, Salem

Are you a citizen of Oregon? . . Date on which sample is sent 2/9/46

Name (or names) of owners of the property. Freers Lumber Co.

Name of particular claim and date of location.

Location of property or source of sample (describe as accurately as possible below):

(1) County . . Marion Canyon Cr., E. branch (2) Mining district

(3) Township 9 S. (4) Range 3 E. (5) Section 6 . . (6) Quarter Section N $\frac{1}{2}$ either NW or NE

How far from passable road? . . from N. side of road.

For what minerals or elements do you wish the sample analyzed? Check Al₂O₃, SiO₂, Fe also petrographic.

(Unless other minerals or elements are specifically named this sample will be assayed for gold and silver only.)

Type of sampling: Channel (length) Grab . . Pipe

Report mailed Called for

IMPORTANT: A sample, to be of value, should be taken in an even channel across the vein from wall to wall. Its position in the workings should be marked and the width measured. Assays of unlocated samples, without widths, are of little value; they create little interest in the minds of experienced investors and engineers.

(signed)

DO NOT WRITE BELOW THIS LINE--FOR OFFICE USE ONLY -- USE OTHER SIDE IF DESIRED

Description

White gibbsite; gray kaolinite.

Sample Number	GOLD		SILVER		Silica Percent	Alumina Percent	Iron Percent
	oz./ T	Value	oz./ T	Value			
<u>P-4435</u>					<u>37.32</u>	<u>49.16</u>	<u>0.49</u>

Report issued() Card filed()