





SAMPLE SECTION	AVG. WIDTH	AVERAGE ANALYSES					VALUE PER TON
		Oz. Au	Oz. Ag	% Cu	% Pb	% Zn	
1	3.9'	0.20	4.14	1.26	2.08	6.00	\$34.74
2	2.0'						11.33
3	2.2'						22.64
4	2.6'	0.36	2.45	2.5	2.15	5.0	
5	1.2'						
6	2.3'	0.12	4.9	2.18	1.46	5.09	
7	2.1'	0.28	3.7	0.74	2.86	4.10	9.37
8	1.9'						31.25
9	1.4'						
10	2.0'	0.59	7.71	3.3	1.08	1.65	
11	2.8'	1.44	4.24	0.75	1.29	0.60	
12	1.8'	1.84	8.71	4.20	1.78	0.65	
13	3.1'	0.50	7.62	2.55	4.48	0.25	
14	1.1'	0.45	3.85	1.10	1.29	1.40	64.65
15	1.8'						12.85
16	1.7'						




EXPLANATION

-  SAMPLED ORE SHOOTS
-  STOPES
-  WASTE FILL IN STOPES

SECTION ADAPTED FROM MAPS  
 SUPPLIED BY F.J. BARTELS  
 SAMPLING AND ASSAYS SHOWN  
 ARE THOSE OBTAINED BY H & H MINES CO., 1939-42

PLANE OF PROJECTION N 65° W

SCALE



MARCH 1947  
 W. Taber

FIG. 4 LONGITUDINAL SECTION, CHAMPION MINE, LANE COUNTY, OREGON

*Handwritten notes:*  
 A-137  
 7-18-47  
 [Signature]